

FBSPET50-W80AD

Face Material

weight	thickness	material
70g / m ² ± 10% ISO536	0.050mm ± 10% ISO534	Bright silver polyester film

Liner

80g / m ² ± 10% ISO536	0.065mm ± 10% ISO534	white glassine paper with super calender treatment
-----------------------------------	----------------------	--

Adhesive

AD is a removable adhesive with high resilience of appropriate initial viscosity, excellent wetting ability on the surface of the object to be pasted, and good final removability and viscosity. It can be repeatedly torn and pasted on many non-paper stickers without leaving residual glue. The normal temperature range is wide.

Peel adhesion

initial adhesion 6 N/25mm or tear off FTM9	20 mins Peel adhesion value on steel at 180 angle 3.0 N/25mm or tear off FTM1	20 mins Peel adhesion value on steel at 90 angle 2N/25mm or tear off FTM2
---	---	---

Temperature

Min. Appl. Temp. 5 °C	Service Temp. -20°C +60°C (24H after labeling)
-----------------------	--

Applications

The product has excellent tensile strength, tear strength, stable physical and chemical properties, opaque, and has certain shading and barrier properties. It has the removable performance of repeated pasting on many pasted products, and is widely used in special fields such as sanitary napkin sealing paste, kitchen utensils and household appliances. Due to the different surface properties of the objects to be pasted, it is recommended to carry out label pasting test on the objects to be pasted before putting them into use. Stable size and chemical corrosion resistance, suitable for making various durability labels.

The above suggestion, application, and elaboration are not intended as the guarantee of Jinya. All sales of Jinya products shall be tested by customer in the final environment to confirm compliance with the requirements of the use of environment.

Printing Methods

A special coating with printability on the surface is suitable for flexographic, letterpress and other printing methods and inks. The ink test before printing is necessary. It can be used for high-speed overprinting, die-cutting and waste disposal on the rotary machine. It is necessary to avoid material deformation or glue failure due to excessive hot knife temperature during processing.

Shelf life

12 months, applicable only to the material delivered by Jinya which has not undergone further processing, under the following **STORAGE CONDITIONS**:

- This material must be stored at a temperature of 23 ± 2°C and 50 ± 5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.